

POLIPOM LUB C 100 TF2

(POM+PTFE)

Poliblend S.p.a.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	3100	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Yield strain	5	%	ISO 527
Strain at break	15	%	ISO 527
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	175	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	150	°C	ISO 75-1/-2
Electrical properties			
ISO Data			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Other properties			
Density	1480	kg/m ³	ISO 1183

Characteristics**Additives**

Lubricants

Features

Copolymer

Chemical Resistance

General Chemical Resistance

Regional Availability

Europe