

**Tecoform® PO20 NL RT**  
(POM+PTFE)

Eurotec Mühendislik Plastikleri

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2500</b>	MPa	ISO 527
Yield stress	<b>50</b>	MPa	ISO 527
Izod notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength Temperature	<b>6</b> <b>-30</b>	kJ/m <sup>2</sup> °C	ISO 180/1A -

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>165</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>100</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	<b>HB</b> <b>1.6</b>	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	<b>HB</b> <b>0.8</b>	class mm	IEC 60695-11-10 -

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	<b>1E12</b>	Ohm*m	IEC 62631-3-1
Surface resistivity	<b>&gt;1E15</b>	Ohm	IEC 62631-3-2
Comparative tracking index	<b>600</b>	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Humidity absorption	<b>0.2</b>	%	Sim. to ISO 62
Density	<b>1500</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>100 - 120</b>	°C	-
Pre-drying - Time	<b>3 - 6</b>	h	-
Melt temperature	<b>180 - 220</b>	°C	-
Mold temperature	<b>60 - 100</b>	°C	-
Feed temperature	<b>30 - 50</b>	°C	-
Holding pressure	<b>80 - 100</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Regional Availability**

Europe