

**LATIBLEND 5262**

(PP+PA6)

LATI Industria Termoplastici S.p.A.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	1.5	%	ISO 294-4, 2577
Molding shrinkage, normal	1.6	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	750	MPa	ISO 527
Yield stress	22	MPa	ISO 527
Yield strain	6	%	ISO 527
Stress at break	20	MPa	ISO 527
Strain at break	150	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	30	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	45	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	80	°C	ISO 75-1/-2
Vicat softening temperature, B	70	°C	ISO 306
Coeff. of linear therm. expansion, parallel	155	E-6/K	ISO 11359-1/-2
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Surface Resistivity	1E12	Ohm	ASTM D 257
<b>Other properties</b>			
Density	940	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3	h	-
Melt temperature	220 - 240	°C	-
Mold temperature	70 - 80	°C	-

**Characteristics****Processing**

Injection Molding

**Features**

Homopolymer

**Special Characteristics**

High impact or impact modified

**Regional Availability**

Europe