

## Polywood S3 20 PP 48 A3 32 PET

(PP+PET)-W20

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>3500</b>	MPa	ISO 527
Tensile Strength	<b>19</b>	MPa	ISO 527
Strain at break	<b>1.8</b>	%	ISO 527
Charpy impact strength, +23°C	<b>15</b>	kJ/m <sup>2</sup>	ISO 179/1eU

### Characteristics

#### Processing

Injection Molding

#### Delivery form

Pellets

#### Certifications

Contains renewable resources

#### Applications

Automotive

#### Regional Availability

Europe