

**Product Texts**

NORYL GTX™ NX0031 resin is a non-reinforced alloy of PPE/PA. This conductive, injection moldable grade exhibits high heat resistance, excellent chemical resistance, and high impact resistance. NORYL NX0031 resin was designed for electrostatic painting and powder coating without the need for a conductive primer. This material can also be solvent painted and is an excellent candidate for exterior, painted applications such as trim and fairings for outdoor vehicles, motorcycle, heavy truck, bus, personal watercraft, and marine. It is available only in black.

UL Yellow Card Link [E121562-533883](https://www.ulprospector.com/usa/Products/121562-533883)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	8	cm <sup>3</sup> /10min	ISO 1133
Temperature	280	°C	-
Load	5	kg	-
Thermal conductivity of melt	0.22	W/(m K)	-
Spec. heat capacity of melt	2200	J/(kg K)	-
Ejection temperature	130	°C	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	280	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2000	MPa	ISO 527
Yield stress	50	MPa	ISO 527
Yield strain	4	%	ISO 527
Stress at break	48	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus	1900	MPa	ISO 178
Charpy notched impact strength, +23°C	18	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	10	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C, 4mm	20	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -30°C, 4mm	10	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	2250	MPa	ASTM D 638
Tensile Strength at Yield	52	MPa	ASTM D 638
Tensile Strength at Break	48	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Elongation at Break	34	%	ASTM D 638
Flexural Modulus	2100	MPa	ASTM D 790
Izod Impact notched, 1/8 in	224	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	117	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Vicat softening temperature, B	175	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	180	°C	ISO 306
Coeff. of linear therm. expansion, parallel	100	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	90	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
<b>ASTM Data</b>			
DTUL @ 66 psi	176	°C	ASTM D 648
DTUL @ 264 psi	136	°C	ASTM D 648
Vicat Temperature	175	°C	ASTM D 1525

**NORYL GTX™ Resin NX0031 - Americas**

(PPE+PA\*)

Saudi Basic Industries Corporation (SABIC)

Other properties	Value	Unit	Test Standard
Water absorption	4.2	%	Sim. to ISO 62
Humidity absorption	1.2	%	Sim. to ISO 62
Density	1090	kg/m <sup>3</sup>	ISO 1183
Density	1090	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	95 - 105	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.07	%	-
Melt temperature	270 - 295	°C	-
Mold temperature	65 - 95	°C	-
Zone 1	255 - 295	°C	-
Zone 2	260 - 295	°C	-
Zone 3	265 - 295	°C	-
Screw speed	20 - 100	rpm	-
Back pressure	0.3 - 1.4	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America