

RamLloy PNP300G6NT

(PPE+PP)-GF30

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	6500	MPa	ISO 527
Tensile Strength	85	MPa	ISO 527
Strain at break	3.8	%	ISO 527
Flexural modulus, 23°C	5400	MPa	ISO 178
Flexural strength	145	MPa	ISO 178
Charpy notched impact strength, +23°C	11	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	13	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	138	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	156	°C	ISO 75-1/-2
Other properties			
Water absorption	0.2	%	Sim. to ISO 62
Density	1180	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	65 - 75	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.02	%	-
Mold temperature	40 - 65	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	245 - 290	°C	-
Zone 2	250 - 290	°C	-
Zone 3	255 - 290	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Natural Color

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa