

XYRON™ X423V

(PPE+PS)-(GF+MD)30

Asahi Kasei

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Burning Behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	1.2	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1230	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa