

XYRON™ X444V

(PPE+PS)-(GF+MD)35

Asahi Kasei

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
[C]: CAMPUS			

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-1	class	IEC 60695-11-10
Thickness tested	1.4	mm	-
[C]: CAMPUS			

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
[C]: CAMPUS			

Other properties	Value	Unit	Test Standard
^[C] Density	1390	kg/m ³	ISO 1183
[C]: CAMPUS			

Characteristics**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa