

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	100	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	21.6	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Thermal conductivity of melt	0.18	W/(m K)	-
Mechanical properties			
ISO Data			
Tensile Modulus	2500	MPa	ISO 527
Tensile Strength	60	MPa	ISO 527
Yield strain	6	%	ISO 527
Flexural strength	105	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	13	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	98	°C	ISO 75-1/-2
Vicat softening temperature, B	116	°C	ISO 306
Coeff. of linear therm. expansion, parallel	65	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
Other properties			
Density	1090	kg/m ³	ISO 1183

Characteristics

Special Characteristics

Flame retardant, Halogen-free

Regional Availability

North America, Europe, Asia Pacific

Applications

Automotive, Electrical and Electronical