

NORYL™ Resin EFN4230 - Asia
(PPE+PS)

Saudi Basic Industries Corporation (SABIC)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	14.2	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	2800	MPa	ASTM D 790
Flexural Strength	119	MPa	ASTM D 790
Izod Impact notched, 1/8 in	31	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

Transparent

Regional Availability

Asia Pacific

Certifications

Food contact, Food approval FDA 21 CFR