

**NORYL™ Resin N1050 - Asia**

(PPE+PS)

Saudi Basic Industries Corporation (SABIC)

**Product Texts**

NORYL™ N1050 resin is a non-reinforced blend of polyphenylene ether (PPE) + high impact polystyrene (HIPS). This injection moldable grade was designed for improved dimensional stability and flow. This grade contains non-brominated, non-chlorinated flame retardant and carries a UL94 flame rating of 5VA at 2.5mm and V0 at 1.5mm along with impact strength, very low moisture absorption, excellent dimensional stability, and good electrical properties. NORYL N1050 resin is an excellent candidate for a variety of applications requiring electrically insulating properties, low moisture absorption and low warpage.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	17	g/10min	ASTM D 1238
Temperature	250	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Flexural Modulus	2530	MPa	ASTM D 790
Flexural Strength	98	MPa	ASTM D 790
Izod Impact notched, 1/8 in	117	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	2.5	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Dissipation Factor, 60 Hz	0.003	-	ASTM D 150
Dielectric Constant, 60 Hz	2.78	-	ASTM D 150
Surface Resistivity	>1E15	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1100	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 80	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	250 - 275	°C	-
Mold temperature	55 - 75	°C	-
Zone 1	215 - 265	°C	-
Zone 2	225 - 270	°C	-
Zone 3	240 - 275	°C	-
Screw speed	20 - 100	rpm	-
Back pressure	0.3 - 0.7	MPa	-

**Characteristics****Processing**

Injection Molding

**Additives**

Flame retarding agent

**Special Characteristics**

Flame retardant

**Applications**

Automotive

**Regional Availability**

Asia Pacific