

Product Texts

NORYL™ PX1134 resin is a non-reinforced blend of polyphenylene ether (PPE) + high impact polystyrene (HIPS). This impact modified, injection moldable grade was developed for automotive interior applications requiring Standard ECE Dashboard Impact Test. NORYL PX1134 resin offers high heat resistance, good impact resistance, low specific gravity, and dimensional stability. It is available only in a variety of colors.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	10	cm ³ /10min	ISO 1133
Temperature	280	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2100	MPa	ISO 527
Yield stress	40	MPa	ISO 527
Yield strain	3	%	ISO 527
Stress at break	40	MPa	ISO 527
Strain at break	40	%	ISO 527
Flexural modulus	1900	MPa	ISO 178
Charpy notched impact strength, +23°C	19	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	14	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C, 4mm	18	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C, 4mm	10	kJ/m ²	ISO 180/1A
Ball indentation hardness	80	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, A	130	°C	ISO 306
Vicat softening temperature, B	115	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	125	°C	ISO 306
Thermal Conductivity	0.23	W/(m K)	DIN 52616

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	2.6	-	IEC 62631-2-1
Dissipation factor, 1MHz	9	E-4	IEC 62631-2-1
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Water absorption	0.14	%	Sim. to ISO 62
Humidity absorption	0.06	%	Sim. to ISO 62
Density	1060	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	2 - 3	h	-
Melt temperature	280 - 300	°C	-
Mold temperature	80 - 120	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	240 - 260	°C	-
Zone 2	260 - 280	°C	-
Zone 3	280 - 300	°C	-

Characteristics

NORYL™ Resin PX1134 - Europe

(PPE+PS)

Saudi Basic Industries Corporation (SABIC)

Processing

Injection Molding

Applications

Automotive

Special Characteristics

High impact or impact modified

Regional Availability

Europe