# NORYL™ Resin PX2630 - Asia

(PPE+PS) Saudi Basic Industries Corporation (SABIC)

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|---|---|---|---|
| **ASTM Data** | | | |
| Melt Flow Index, MFI | **3.8** | g/10min | ASTM D 1238 |
| Temperature | **250** | °C | - |
| Load | **10** | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|---|---|---|---|
| **ASTM Data** | | | |
| Flexural Modulus | **2090** | MPa | ASTM D 790 |
| Flexural Strength | **76** | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | **330** | J/m | ASTM D 256 |

| Other properties | Value | Unit | Test Standard |
|---|---|---|---|
| Density | **1060** | kg/m³ | ASTM D 792 |

## Characteristics

**Chemical Resistance**

Hydrolytically Stable

**Regional Availability**

Asia Pacific


Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.