

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	43	MPa	ISO 527
Flexural modulus, 23°C	2370	MPa	ISO 178
Flexural strength	72	MPa	ISO 178
Charpy notched impact strength, +23°C	18	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	104	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	75	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB 1.6	class mm	IEC 60695-11-10 -
ASTM Data			
DTUL @ 264 psi	110	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	2.8	-	IEC 62631-2-1
Relative permittivity, 1MHz	2.8	-	IEC 62631-2-1
Dissipation factor, 100Hz	5	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	6	E-4	IEC 62631-2-1
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1
Surface resistivity	1E16	Ohm	IEC 62631-3-2
Electric strength	29	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	240 - 290	°C	-
Mold temperature	50 - 80	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific