

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	74	MPa	ISO 527
Flexural modulus, 23°C	2440	MPa	ISO 178
Flexural strength	110	MPa	ISO 178
^[C] Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	129	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	2.0	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	2.9	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	2.9	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	4	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	5	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.1	%	Sim. to ISO 62
^[C] Density	1100	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	260 - 320	°C	-
Mold temperature	60 - 100	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa