

Product Texts

LNP STAT-KON ZE002 compound is based on Polyphenylene Ether / Polystyrene (PPE/PS) blend containing 10% carbon fiber. Added features of this grade include: Electrically Conductive.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	104	MPa	ISO 527
Strain at break	1.6	%	ISO 527
Flexural modulus	5500	MPa	ISO 178
Izod impact strength, +23°C, 4mm	15	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	5	kJ/m ²	ISO 180/1A

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	10000	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1110	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Melt temperature	300 - 305	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	275 - 290	°C	-
Zone 2	290 - 300	°C	-
Zone 3	300 - 310	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity