

NORYL™ Resin PX138H - Asia

(PPE+PS)-GF20

Saudi Basic Industries Corporation (SABIC)

Product Texts

NORYL™ PX138H resin is a 20% glass reinforced blend of polyphenylene ether (PPE) + high impact polystyrene (HIPS). This injection moldable grade exhibits very low moisture absorption, high strength, hydrolytic stability, Low warpage, low specific gravity, and dimensional stability.

UL Yellow Card Link [E207780-228575](https://www.ul.com/yellow-card/E207780-228575)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	2	cm ³ /10min	ISO 1133
Temperature	280	°C	-
Load	5	kg	-
ASTM Data			
Melt Flow Index, MFI	2.7	g/10min	ASTM D 1238
Temperature	280	°C	-
Load	5	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	6000	MPa	ISO 527
Yield stress	90	MPa	ISO 527
Yield strain	3	%	ISO 527
Stress at break	90	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus	5400	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C, 4mm	30	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C, 4mm	33	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	6500	MPa	ASTM D 638
Tensile Strength at Yield	100	MPa	ASTM D 638
Tensile Strength at Break	100	MPa	ASTM D 638
Elongation at Yield	3	%	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	5300	MPa	ASTM D 790
Izod Impact notched, 1/8 in	90	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	100	J/m	ASTM D 256
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	135	°C	ISO 75-1/-2
Vicat softening temperature, B	143	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	147	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
ASTM Data			
DTUL @ 264 psi	137	°C	ASTM D 648
Vicat Temperature	143	°C	ASTM D 1525
Other properties			
Water absorption	0.12	%	Sim. to ISO 62
Humidity absorption	0.04	%	Sim. to ISO 62
Density	1230	kg/m ³	ISO 1183
Density	1230	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	110 - 120	°C	-
Pre-drying - Time	3 - 4	h	-

NORYL™ Resin PX138H - Asia

(PPE+PS)-GF20

Saudi Basic Industries Corporation (SABIC)

Processing humidity	≤0.02	%	-
Melt temperature	300 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	265 - 315	°C	-
Zone 2	275 - 320	°C	-
Zone 3	290 - 325	°C	-
Screw speed	20 - 100	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific

Chemical Resistance

Hydrolytically Stable