

IUPIACE GH30
(PPE+PS)-GF30

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	2.7	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8900	MPa	ISO 527
Stress at break	103	MPa	ISO 527
Strain at break	1.3	%	ISO 527
Flexural modulus, 23°C	8400	MPa	ISO 178
Flexural strength	170	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	130	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	142	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	25	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	60	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	3E14	Ohm*m	IEC 62631-3-1
Surface resistivity	6E15	Ohm	IEC 62631-3-2
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	150	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	0.06	%	Sim. to ISO 62
Density	1310	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	2 - 4	h	-
Mold temperature	90 - 120	°C	-
Zone 1	260 - 290	°C	-
Zone 2	280 - 310	°C	-
Zone 3	280 - 310	°C	-
Nozzle temperature	270 - 310	°C	-
Screw speed	60 - 150	rpm	-
Injection pressure	20 - 150	MPa	-

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant

Applications

Automotive, Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa