

**IUPIACE GV30**  
(PPE+PS)-GF30

Mitsubishi Engineering-Plastics Corporation

| Processing/Physical Characteristics | Value | Unit                   | Test Standard   |
|-------------------------------------|-------|------------------------|-----------------|
| <b>ISO Data</b>                     |       |                        |                 |
| Melt volume-flow rate, MVR          | 3     | cm <sup>3</sup> /10min | ISO 1133        |
| Temperature                         | 300   | °C                     | -               |
| Load                                | 2.16  | kg                     | -               |
| Molding shrinkage, parallel         | 0.1   | %                      | ISO 294-4, 2577 |
| Molding shrinkage, normal           | 0.3   | %                      | ISO 294-4, 2577 |

| Mechanical properties                 | Value | Unit              | Test Standard |
|---------------------------------------|-------|-------------------|---------------|
| <b>ISO Data</b>                       |       |                   |               |
| Tensile Modulus                       | 8400  | MPa               | ISO 527       |
| Stress at break                       | 110   | MPa               | ISO 527       |
| Strain at break                       | 1.5   | %                 | ISO 527       |
| Flexural modulus, 23°C                | 8300  | MPa               | ISO 178       |
| Flexural strength                     | 170   | MPa               | ISO 178       |
| Charpy notched impact strength, +23°C | 9     | kJ/m <sup>2</sup> | ISO 179/1eA   |

| Thermal properties                          | Value | Unit  | Test Standard   |
|---|-------|-------|-----------------|
| <b>ISO Data</b>                             |       |       |                 |
| Temp. of deflection under load, 1.80 MPa    | 135   | °C    | ISO 75-1/-2     |
| Temp. of deflection under load, 0.45 MPa    | 140   | °C    | ISO 75-1/-2     |
| Coeff. of linear therm. expansion, parallel | 25    | E-6/K | ISO 11359-1/-2  |
| Coeff. of linear therm. expansion, normal   | 60    | E-6/K | ISO 11359-1/-2  |
| Burning behav. at thickness h               | V-1   | class | IEC 60695-11-10 |
| Thickness tested                            | 0.8   | mm    | -               |
| Yellow Card available                       | yes   | -     | -               |

| Electrical properties      | Value | Unit  | Test Standard |
|----------------------------|-------|-------|---------------|
| <b>ISO Data</b>            |       |       |               |
| Volume resistivity         | 3E14  | Ohm*m | IEC 62631-3-1 |
| Surface resistivity        | 6E15  | Ohm   | IEC 62631-3-2 |
| Comparative tracking index | 200   | -     | IEC 60112     |

| Other properties | Value | Unit              | Test Standard  |
|------------------|-------|-------------------|----------------|
| Water absorption | 0.06  | %                 | Sim. to ISO 62 |
| Density          | 1310  | kg/m <sup>3</sup> | ISO 1183       |

| Processing Recommendation Injection Molding | Value     | Unit | Test Standard |
|---|-----------|------|---------------|
| Pre-drying - Temperature                    | 100 - 120 | °C   | -             |
| Pre-drying - Time                           | 2 - 4     | h    | -             |
| Mold temperature                            | 90 - 125  | °C   | -             |
| Zone 1                                      | 260 - 290 | °C   | -             |
| Zone 2                                      | 280 - 310 | °C   | -             |
| Zone 3                                      | 280 - 310 | °C   | -             |
| Nozzle temperature                          | 270 - 310 | °C   | -             |
| Screw speed                                 | 60 - 150  | rpm  | -             |
| Injection pressure                          | 20 - 150  | MPa  | -             |

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Flame retardant

**Applications**

Automotive, Electrical and Electronical, General Purpose

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa