

LNP™ THERMOCOMP™ Compound ZF006 - Europe

(PPE+PS)-GF30

Saudi Basic Industries Corporation (SABIC)

Product Texts

LNP THERMOCOMP ZF006 compound is based on Polyphenylene Ether / Polystyrene (PPE/PS) blend containing 30% glass fiber.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8500	MPa	ISO 527
Stress at break	102	MPa	ISO 527
Strain at break	1.6	%	ISO 527
Flexural modulus	6900	MPa	ISO 178
Izod impact strength, +23°C, 4mm	25	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	8	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	132	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	137	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	29	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	64	E-6/K	ISO 11359-1/-2

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Melt temperature	300 - 305	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	275 - 290	°C	-
Zone 2	290 - 300	°C	-
Zone 3	300 - 310	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe