

**LURANYL® KR 2403 G6**

(PPE+PS)-GF30

Romira GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>9</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>250</b>	°C	-
Load	<b>21.6</b>	kg	-
Molding shrinkage, parallel	<b>0.3</b>	%	ISO 294-4, 2577
Thermal conductivity of melt	<b>0.23</b>	W/(m K)	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>9000</b>	MPa	ISO 527
Tensile Strength	<b>110</b>	MPa	ISO 527
Strain at break	<b>2.5</b>	%	ISO 527
Flexural strength	<b>160</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>35</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	<b>35</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>14</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	<b>13</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>141</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>145</b>	°C	ISO 306
Coeff. of linear therm. expansion, parallel	<b>35</b>	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Yellow Card available	<b>yes</b>	-	-
<b>Other properties</b>			
Density	<b>1280</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Low Warpage

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific