

XYRON™ VTD1V
(PPE+PS)-MD10

Asahi Kasei

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| ^[C] Charpy notched impact strength, +23°C | 20 | kJ/m ² | ISO 179/1eA |

[C]: CAMPUS

| Electrical properties | Value | Unit | Test Standard |
|------------------------------------|-----------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Volume resistivity | >1E13 | Ohm*m | IEC 62631-3-1 |
| ^[C] Surface resistivity | >1E15 | Ohm | IEC 62631-3-2 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| ^[C] Density | 1130 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics

Regional Availability

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa