

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA
^[C] : CAMPUS			

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
^[C] : CAMPUS			

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] : CAMPUS			

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.06	%	Sim. to ISO 62
^[C] Density	1250	kg/m ³	ISO 1183
^[C] : CAMPUS			

Characteristics

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa