

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	61	MPa	ISO 527
Flexural modulus, 23°C	4600	MPa	ISO 178
Flexural strength	117	MPa	ISO 178
^[C] Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	118	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	50	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-1	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	2.5	mm	-

ASTM Data

DTUL @ 264 psi	120	°C	ASTM D 648
----------------	------------	----	------------

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.2	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.1	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	3	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	5	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.06	%	Sim. to ISO 62
^[C] Density	1230	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 110	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	250 - 300	°C	-
Mold temperature	70 - 90	°C	-

Characteristics

Processing

Injection Molding

Features

Low Warpage

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa