

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA
^[C] : CAMPUS			

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-1	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
^[C] : CAMPUS			

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.3	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	6	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	8	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] : CAMPUS			

Other properties	Value	Unit	Test Standard
^[C] Density	1340	kg/m ³	ISO 1183
^[C] : CAMPUS			

Characteristics

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa