

**Product Texts**

LNP LUBRICOMP ZL003 compound is based on Polyphenylene Ether / Polystyrene (PPE/PS) blend containing 15% PTFE. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E45329-101358187](https://www.ulprospector.com/usa/Products/Plastics/Engineering-Plastics/101358187)

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2250</b>	MPa	ISO 527
Stress at break	<b>48</b>	MPa	ISO 527
Strain at break	<b>8.3</b>	%	ISO 527
Flexural modulus	<b>2000</b>	MPa	ISO 178
Izod impact strength, +23°C, 4mm	<b>17</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	<b>5</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>119</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>130</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>79</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	<b>81</b>	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1150</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>120</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Melt temperature	<b>300 - 305</b>	°C	-
Mold temperature	<b>80 - 110</b>	°C	-
Zone 1	<b>275 - 290</b>	°C	-
Zone 2	<b>290 - 300</b>	°C	-
Zone 3	<b>300 - 310</b>	°C	-
Screw speed	<b>30 - 60</b>	rpm	-
Back pressure	<b>0.2 - 0.3</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Europe