

FORMPOLY PPOGT30G

(PPO+PA*)-GF20

Formulated Polymers Limited

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	155	MPa	ASTM D 638
Elongation at Break	4	%	ASTM D 638
Flexural Modulus	7000	MPa	ASTM D 790
Flexural Strength	220	MPa	ASTM D 790
Izod Impact notched, 1/8 in	83.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	225	°C	ASTM D 648
Vicat Temperature	240	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Water Absorption, Equilibrium	3.6	%	ASTM D 570
Density	1310	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Applications

Automotive

Features

Low Odor, Low Warpage

Regional Availability

Asia Pacific