

**FRHIPS-960PC**

(PS-HI)

Kingfa Sci. &amp; Tech.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>8</b>	g/10min	ASTM D 1238
Temperature	<b>200</b>	°C	-
Load	<b>5</b>	kg	-
Mold Shrinkage, MD	<b>0.005</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>21</b>	MPa	ASTM D 638
Elongation at Break	<b>35</b>	%	ASTM D 638
Flexural Modulus	<b>2000</b>	MPa	ASTM D 790
Flexural Strength	<b>35</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>90.3</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>3.2</b>	mm	-
DTUL @ 264 psi	<b>80</b>	°C	ASTM D 648
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Volume Resistivity	<b>&gt;1E15</b>	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Density	<b>1180</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Applications**

IT / Business Machine, Electrical and Electronical

**Delivery form**

Pellets

**Regional Availability**

Asia Pacific

**Special Characteristics**

Flame retardant, U.V. stabilized or stable to weather, Heat stabilized or stable to heat