

**RTP 4300 S-1010**

(PSU+PC)-GF10

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.004</b>	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	<b>3792</b>	MPa	ASTM D 638
Tensile Strength	<b>82.7</b>	MPa	ASTM D 638
Flexural Modulus	<b>3447</b>	MPa	ASTM D 790
Flexural Strength	<b>131</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>64.1</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-1</b>	-	UL 94
Thickness tested	<b>1.59</b>	mm	-
DTUL @ 264 psi	<b>154</b>	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	<b>0.2</b>	%	ASTM D 570
Density	<b>1290</b>	kg/m <sup>3</sup>	ASTM D 792
Moisture Content	<b>0.02</b>	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>121</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Melt temperature	<b>282 - 327</b>	°C	-
Mold temperature	<b>65.6 - 98.9</b>	°C	-
Injection pressure	<b>68.9 - 103</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific