

**Dryflex® AM 55A202B**  
(SB+SEBS)

Hexpol TPE

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>3</b>	MPa	ISO 37
Tear strength	<b>15</b>	kN/m	ISO 34-1
Abrasion resistance	<b>500</b>	mm <sup>3</sup>	ISO 4649

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1100</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Mold temperature	<b>20 - 60</b>	°C	-
Feed temperature	<b>170 - 190</b>	°C	-
Zone 1	<b>180 - 200</b>	°C	-
Zone 2	<b>190 - 210</b>	°C	-
Zone 3	<b>200 - 220</b>	°C	-

**Characteristics**

**Processing**

Injection Molding

**Chemical Resistance**

General Chemical Resistance, Solvent Resistance

**Special Characteristics**

U.V. stabilized or stable to weather

**Applications**

Automotive

**Features**

Anti Slip, Low Fogging, Low Odor, Scratch Resistant

**Regional Availability**

North America, Europe, Asia Pacific