

Product Texts

LNP LUBRICOMP YP003 compound is based on Polyester Elastomer resin containing 15% PTFE/silicone. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E45329-101344692](https://www.ulprospector.com/usa/Products/Plastics/101344692)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
Molding shrinkage, normal	2.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	200	MPa	ISO 527
Yield stress	20	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus	200	MPa	ISO 178
Izod impact strength, +23°C, 4mm	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	30	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

Other properties	Value	Unit	Test Standard
Density	1260	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.1	%	-
Melt temperature	215 - 240	°C	-
Mold temperature	25 - 55	°C	-
Zone 1	180 - 195	°C	-
Zone 2	205 - 215	°C	-
Zone 3	225 - 240	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe