

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	60	cm <sup>3</sup> /10min	ISO 1133
Temperature	240	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	8100	MPa	ISO 527
Stress at break	130	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural strength	180	MPa	ISO 178
Charpy impact strength, +23°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	35	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	6	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	185	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	175	°C	ISO 75-1/-2
Vicat softening temperature, A	125	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
Surface resistivity	1E12	Ohm	IEC 62631-3-2
Comparative tracking index	600	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	4.5	%	Sim. to ISO 62
Humidity absorption	1.5	%	Sim. to ISO 62
Density	1280	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Melt temperature	240 - 260	°C	-
Mold temperature	70 - 90	°C	-

## Characteristics

### Processing

Injection Molding

### Special Characteristics

U.V. stabilized or stable to weather

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa