

**Product Texts**

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Special Features	good flow, processing stabilised
Market Segment	Medical / Personal Care, packaging, various
Application Area	interior decoration / finishing, hygiene products, various
Typical Applications	housings, washer bottles, various

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
--	-------	------	---------------

**ISO Data**

<sup>[C]</sup> Melt volume-flow rate, MVR	22	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

[C]: CAMPUS

**Mechanical properties**

	Value	Unit	Test Standard
--	-------	------	---------------

**ISO Data**

<sup>[C]</sup> Tensile Modulus	1900	MPa	ISO 527
<sup>[C]</sup> Yield stress	35	MPa	ISO 527
<sup>[C]</sup> Yield strain	2.6	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	100	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	17	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	Value	Unit	Test Standard
--	-------	------	---------------

**ISO Data**

<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	81	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	95	°C	ISO 306

[C]: CAMPUS

**Other properties**

	Value	Unit	Test Standard
--	-------	------	---------------

<sup>[C]</sup> Density	1060	kg/m <sup>3</sup>	ISO 1183
------------------------	------	-------------------	----------

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Applications**

Medical, Packaging

**Features**

Copolymer

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Other text information****Injection molding**

Pre-Drying Conditions	80 °C in an air circulating dryer for 3-6 h 80 °C in a dry air (dessiccant) dryer for 2-4 h
-----------------------	--

Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------