

Dialac® AVR300

ABS

Techno-UMG Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	12	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	1750	MPa	ISO 527
Tensile Strength	36	MPa	ISO 527
Flexural modulus, 23°C	1850	MPa	ISO 178
Flexural strength	55	MPa	ISO 178
Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 86	-	ISO 2039-2
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	71	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	100	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	2.2	mm	-
Other properties			
Density	1210	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Asia Pacific