

Dialac® S710A

ABS

Techno-UMG Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	3	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1550	MPa	ISO 527
Tensile Strength	33	MPa	ISO 527
Flexural modulus, 23°C	1650	MPa	ISO 178
Flexural strength	50	MPa	ISO 178
Charpy notched impact strength, +23°C	35	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 82	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	77	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	95	E-6/K	ISO 11359-1/-2

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Asia Pacific