

**Novodur® 240**

ABS

INEOS Styrolution

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>20</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>220</b>	°C	-
Load	<b>10</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Yield stress	<b>49</b>	MPa	ISO 527

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Vicat Temperature	<b>100</b>	°C	ASTM D 1525

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Applications**

Electrical and Electronical, Sports Equipment

**Regional Availability**

Asia Pacific