

Product Texts

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Filler/Additive System	15 % special filler
Special Features	highly reflective,opaque
Market Segment	Automotive,various
Application Area	lighting,light blocking components
Typical Applications	light guides,reflectors

Processing/Physical Characteristics

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Melt volume-flow rate, MVR	7	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

[C]: CAMPUS

Mechanical properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Tensile Modulus	2600	MPa	ISO 527
^[C] Yield stress	50	MPa	ISO 527
^[C] Yield strain	2.8	%	ISO 527
^[C] Charpy impact strength, +23°C	73	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	9	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Temp. of deflection under load, 1.80 MPa	93	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	110	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
--	-------	------	---------------

^[C] Density	1170	kg/m ³	ISO 1183
------------------------	------	-------------------	----------

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Light Blocking

Delivery form

White

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions 80 °C in a dry air (dessiccant) dryer
 for 2-4 h
 80 °C in an air circulating dryer
 for 4-8 h
 max. moisture content <0,02 %

Processing Injection Moulding melt temperature 220-260 °C
 mould temperature 50-80 °C

Storage dry, protected from light