

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	6	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1800	MPa	ISO 527
Yield stress	40	MPa	ISO 527
Strain at break	10	%	ISO 527
Flexural modulus, 23°C	1800	MPa	ISO 178
Flexural strength	60	MPa	ISO 178
Charpy notched impact strength, +23°C	30	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	12	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	30	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	12	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	95 <sup>[ann.]</sup>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	91	°C	ISO 75-1/-2
Vicat softening temperature, B	95	°C	ISO 306

ann.: annealed

Other properties	Value	Unit	Test Standard
Density	1040	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	230 - 260	°C	-
Mold temperature	60 - 80	°C	-

## Characteristics

### Processing

Injection Molding, Sheet Extrusion, Blow Molding

### Applications

Sports Equipment, Toys

### Special Characteristics

High impact or impact modified

### Regional Availability

Asia Pacific