

**Novodur® 970**

ABS

INEOS Styrolution

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	22	cm <sup>3</sup> /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	41	MPa	ISO 527

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Vicat Temperature	98	°C	ASTM D 1525

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

High impact or impact modified

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

Asia Pacific