

Tisblend® IH UNR K03 R01

(ABS+PC)

Tisan Engineering Plastics Co.Ltd.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2250	MPa	ISO 527
Stress at break	51.5	MPa	ISO 527
Strain at break	4.5	%	ISO 527
Izod notched impact strength, +23°C	45	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	255	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	108	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ISO 1183
Moisture Content	0.2	%	-

Characteristics**Delivery form**

Pellets, Natural Color

Regional Availability

Europe, Near East/Africa

Special Characteristics

U.V. stabilized or stable to weather