

RamShine PV101GR75

ABS

Polyram

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--------------------------------------|------------|---------|-----------------|
| ISO Data | | | |
| Melt flow index, MFI | 24 | g/10min | ISO 1133 |
| Temperature | 220 | °C | - |
| Load | 10 | kg | - |
| Other Standards^[S] | | | |
| Molding shrinkage, parallel | 0.6 | % | Producer Method |

S: These properties are reported by the producer according standards that are different to our defaults.

| Mechanical properties | Value | Unit | Test Standard |
|-----------------------------|------------|------|---------------|
| ASTM Data | | | |
| Izod Impact notched, 1/8 in | 260 | J/m | ASTM D 256 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------------|-------------------|---------------|
| Density | 1050 | kg/m ³ | ISO 1183 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|---|------------------|------|---------------|
| Pre-drying - Temperature | 80 | °C | - |
| Pre-drying - Time | 2 - 4 | h | - |
| Processing humidity | ≤0.1 | % | - |
| Mold temperature | 40 - 80 | °C | - |
| Feed temperature | 60 - 70 | °C | - |
| Zone 1 | 200 - 220 | °C | - |
| Zone 2 | 200 - 220 | °C | - |
| Zone 3 | 210 - 240 | °C | - |

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa