

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	102	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	107	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	108	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	25	kV/mm	IEC 60243-1
^[C] Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1050	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa