

**TAIRILAC® AF3500**

ABS

Formosa Chemicals &amp; Fibre Corp.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>5</b>	g/10min	ASTM D 1238
Temperature	<b>200</b>	°C	-
Load	<b>5</b>	kg	-
Mold Shrinkage, MD	<b>0.0055</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>38</b>	MPa	ASTM D 638
Flexural Modulus	<b>1960</b>	MPa	ASTM D 790
Flexural Strength	<b>66</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 102</b>	-	ASTM D 785
Izod Impact notched, 1/4 in	<b>291</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
DTUL @ 264 psi	<b>83</b>	°C	ASTM D 648
Vicat Temperature	<b>99</b>	°C	ASTM D 1525
<b>Other properties</b>			
Density	<b>1040</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

High impact or impact modified

**Regional Availability**

Asia Pacific