

**Techno ABS 600 (YT-346)**

ABS

Techno-UMG Co., Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>11</b>	g/10min	ISO 1133
Temperature	<b>220</b>	°C	-
Load	<b>10</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Strength	<b>45</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>2170</b>	MPa	ISO 178
Flexural strength	<b>69</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>19</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Rockwell hardness	<b>R 104</b>	-	ISO 2039-2
<b>ASTM Data</b>			
Tensile Strength	<b>49</b>	MPa	ASTM D 638
Flexural Modulus	<b>2350</b>	MPa	ASTM D 790
Flexural Strength	<b>81.4</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 105</b>	-	ASTM D 785
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
<b>Other properties</b>			
Density	<b>1050</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>1050</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Extrusion</b>			
Pre-drying - Temperature	<b>80 - 90</b>	°C	-
Pre-drying - Time	<b>2 - 5</b>	h	-
Zone 1	<b>170 - 240</b>	°C	-

**Characteristics****Processing**

Profile Extrusion, Other Extrusion, Coating, Blow Molding

**Regional Availability**

North America, Asia Pacific