

Techno ABS 620 (YT-802)

ABS

Techno-UMG Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5.5	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Mechanical properties			
ISO Data			
Tensile Strength	38	MPa	ISO 527
Flexural modulus, 23°C	1750	MPa	ISO 178
Flexural strength	59	MPa	ISO 178
Charpy impact strength, +23°C	28	kJ/m ²	ISO 179/1eU
Rockwell hardness	R 94	-	ISO 2039-2
ASTM Data			
Tensile Strength	42.2	MPa	ASTM D 638
Flexural Modulus	2160	MPa	ASTM D 790
Flexural Strength	69.6	MPa	ASTM D 790
Rockwell Hardness	R 102	-	ASTM D 785
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Other properties			
Density	1050	kg/m ³	ISO 1183
Density	1050	kg/m ³	ASTM D 792
Processing Recommendation Extrusion			
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	2 - 5	h	-
Zone 1	170 - 240	°C	-

Characteristics**Processing**

Other Extrusion

Regional Availability

North America, Asia Pacific

Special Characteristics

High impact or impact modified