

**Techno ABS R790 (TFB310)**

ABS

Techno-UMG Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>16</b>	g/10min	ISO 1133
Temperature	<b>220</b>	°C	-
Load	<b>10</b>	kg	-
Molding shrinkage, parallel	<b>0.5</b>	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	<b>49</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>1950</b>	MPa	ISO 178
Flexural strength	<b>59</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>23</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Rockwell hardness	<b>R 99</b>	-	ISO 2039-2
<b>ASTM Data</b>			
Tensile Strength	<b>52</b>	MPa	ASTM D 638
Flexural Modulus	<b>2300</b>	MPa	ASTM D 790
Flexural Strength	<b>80.4</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 102</b>	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94

Other properties	Value	Unit	Test Standard
Density	<b>1060</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>1060</b>	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>80 - 90</b>	°C	-
Pre-drying - Time	<b>2 - 5</b>	h	-
Mold temperature	<b>40 - 80</b>	°C	-
Zone 1	<b>190 - 260</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Asia Pacific

**Chemical Resistance**

General Chemical Resistance