

Product Texts

Standard ABS, fast flowing with balanced impact strength.
For all kind of moulding parts.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, B	92	°C	ISO 306

Other properties	Value	Unit	Test Standard
Water absorption	1.6	%	Sim. to ISO 62
Density	1060	kg/m ³	ISO 1183

Characteristics

Regional Availability

Europe