

Product Texts

Terluran® ECO GP-22 BC60 is an easy-flow, general purpose injection molding grade with high resistance to impact and heat distortion; intended for a wide range of applications, particularly in the housings sector. Terluran® ECO GP-22 BC60 contains bio-attributed content from styrene monomer from renewable sources, The use of renewable feedstock brings significant product carbon footprint savings. Terluran® ECO GP-22 BC60 is produced according to an ISCC-certified mass balance approach, and has identical physical and mechanical properties as its fossil-based counterpart. All the same regulatory documents are also available.

Terluran ECO GP-22 BC60 is an ISCC compliant product leading to a substitution of fossil source styrene with attributed ISCC certified bio-circular styrene.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	19	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
^[C] Density of melt	927	kg/m ³	-
^[C] Thermal conductivity of melt	0.202	W/(m K)	-
^[C] Spec. heat capacity of melt	2570	J/(kg K)	-
^[C] Ejection temperature	91	°C	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2300	MPa	ISO 527
^[C] Yield stress	45	MPa	ISO 527
^[C] Yield strain	2.6	%	ISO 527
^[C] Nominal strain at break	10	%	ISO 527
Flexural strength	65	MPa	ISO 178
^[C] Charpy impact strength, +23°C	180	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	100	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	22	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	8	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	26	kJ/m ²	ISO 180/1A
Izod notched impact strength	8	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Ball indentation hardness	97	MPa	ISO 2039-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	94	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	99	°C	ISO 75-1/-2
Vicat softening temperature, A	105	°C	ISO 306
^[C] Vicat softening temperature, B	96	°C	ISO 306
Coeff. of linear therm. expansion, parallel	95	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-

Other Standards^[S]

Thermal Conductivity, solid state	0.17	W/(m K)	ISO 22007-4
-----------------------------------	------	---------	-------------

S: These properties are reported by the producer according standards that are different to our defaults. [C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	2.9	-	IEC 62631-2-1

Terluran® ECO GP-22 BC60

ABS

INEOS Styrolution

^[C] Relative permittivity, 1MHz	2.8	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	48	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	79	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	1E13	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	1	%	Sim. to ISO 62
^[C] Humidity absorption	0.22	%	Sim. to ISO 62
^[C] Density	1040	kg/m ³	ISO 1183
Bulk density	600	kg/m ³	-

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	220 - 260	°C	-
Mold temperature	30 - 80	°C	-
Injection speed	200	mm/s	-

Characteristics**Processing**

Injection Molding

Certifications

Contains renewable resources, ISCC Plus

Delivery form

Pellets

Applications

Automotive, General Purpose, Toys

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Near East/Africa

Features

High Gloss

Other text information**Injection molding**

PREPROCESSING

Pre-drying, Temperature: 80°C

Pre-drying, Time: 2 - 4h

PROCESSING

Melt temperature, range: 220 - 260°C

Mold temperature, range: 30 - 80°C