

Product Texts

Terluran® ECO GP-22 BC100 is an easy-flow, general purpose injection molding grade with high resistance to impact and heat distortion; intended for a wide range of applications, particularly in the housings sector. Terluran® ECO GP-22 BC100 is a complete bio-attributed solution with bio-attributed content from all three monomers (styrene monomer, butadiene, and acrylonitrile). The use of renewable feedstock brings significant product carbon footprint savings. Terluran® ECO GP-22 BC100 is produced according to an ISCC-certified mass balance approach, and has identical physical and mechanical properties as its fossil-based counterpart. All the same regulatory documents are also available.

Terluran ECO GP-22 BC100 is an ISCC compliant product leading to a substitution of fossil source styrene, acrylonitrile and butadiene with ISCC certified bio-attributed styrene, acrylonitrile and butadiene.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|---|-------|------------------------|-----------------|
| ISO Data | | | |
| ^[C] Melt volume-flow rate, MVR | 19 | cm ³ /10min | ISO 1133 |
| Temperature | 220 | °C | - |
| Load | 10 | kg | - |
| Molding shrinkage, parallel | 0.6 | % | ISO 294-4, 2577 |
| ^[C] Density of melt | 927 | kg/m ³ | - |
| ^[C] Thermal conductivity of melt | 0.202 | W/(m K) | - |
| ^[C] Spec. heat capacity of melt | 2570 | J/(kg K) | - |
| ^[C] Ejection temperature | 91 | °C | - |

[C]: CAMPUS

| Mechanical properties | Value | Unit | Test Standard |
|--|-------|-------------------|---------------|
| ISO Data | | | |
| ^[C] Tensile Modulus | 2300 | MPa | ISO 527 |
| ^[C] Yield stress | 45 | MPa | ISO 527 |
| ^[C] Yield strain | 2.6 | % | ISO 527 |
| ^[C] Nominal strain at break | 10 | % | ISO 527 |
| Flexural strength | 65 | MPa | ISO 178 |
| ^[C] Charpy impact strength, +23°C | 180 | kJ/m ² | ISO 179/1eU |
| ^[C] Charpy impact strength, -30°C | 100 | kJ/m ² | ISO 179/1eU |
| ^[C] Charpy notched impact strength, +23°C | 22 | kJ/m ² | ISO 179/1eA |
| ^[C] Charpy notched impact strength, -30°C | 8 | kJ/m ² | ISO 179/1eA |
| Izod notched impact strength, +23°C | 26 | kJ/m ² | ISO 180/1A |
| Izod notched impact strength | 8 | kJ/m ² | ISO 180/1A |
| Temperature | -30 | °C | - |
| Ball indentation hardness | 97 | MPa | ISO 2039-1 |

[C]: CAMPUS

| Thermal properties | Value | Unit | Test Standard |
|---|-------|-------|-----------------|
| ISO Data | | | |
| ^[C] Temp. of deflection under load, 1.80 MPa | 94 | °C | ISO 75-1/-2 |
| ^[C] Temp. of deflection under load, 0.45 MPa | 99 | °C | ISO 75-1/-2 |
| Vicat softening temperature, A | 105 | °C | ISO 306 |
| ^[C] Vicat softening temperature, B | 96 | °C | ISO 306 |
| Coeff. of linear therm. expansion, parallel | 95 | E-6/K | ISO 11359-1/-2 |
| ^[C] Burning Behav. at 1.5 mm nom. thickn. | HB | class | IEC 60695-11-10 |
| Thickness tested | 1.5 | mm | - |
| Yellow Card available | yes | - | - |
| ^[C] Burning Behav. at thickness h | HB | class | IEC 60695-11-10 |
| Thickness tested | 3.0 | mm | - |
| Yellow Card available | yes | - | - |

Other Standards^[S]

| | | | |
|-----------------------------------|------|---------|-------------|
| Thermal Conductivity, solid state | 0.17 | W/(m K) | ISO 22007-4 |
|-----------------------------------|------|---------|-------------|

S: These properties are reported by the producer according standards that are different to our defaults. [C]: CAMPUS

| Electrical properties | Value | Unit | Test Standard |
|---|-------|-------|---------------|
| ISO Data | | | |
| ^[C] Relative permittivity, 100Hz | 2.9 | - | IEC 62631-2-1 |
| ^[C] Relative permittivity, 1MHz | 2.8 | - | IEC 62631-2-1 |
| ^[C] Dissipation factor, 100Hz | 48 | E-4 | IEC 62631-2-1 |
| ^[C] Dissipation factor, 1MHz | 79 | E-4 | IEC 62631-2-1 |
| ^[C] Volume resistivity | >1E13 | Ohm*m | IEC 62631-3-1 |
| ^[C] Surface resistivity | 1E13 | Ohm | IEC 62631-3-2 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|------------------------------------|-------|-------------------|----------------|
| ^[C] Water absorption | 1 | % | Sim. to ISO 62 |
| ^[C] Humidity absorption | 0.22 | % | Sim. to ISO 62 |
| ^[C] Density | 1040 | kg/m ³ | ISO 1183 |
| Bulk density | 600 | kg/m ³ | - |

[C]: CAMPUS

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|---|-----------|------|---------------|
| Pre-drying - Temperature | 80 | °C | - |
| Pre-drying - Time | 2 - 4 | h | - |
| Melt temperature | 220 - 260 | °C | - |
| Mold temperature | 30 - 80 | °C | - |
| Injection speed | 200 | mm/s | - |

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

High Gloss

Certifications

Contains renewable resources, ISCC Plus

Applications

Automotive, General Purpose, Toys

Regional Availability

North America, Europe, Near East/Africa

Other text information

Injection molding

PREPROCESSING

Pre-drying, Temperature: 80°C

Pre-drying, Time: 2 - 4h

PROCESSING

Melt temperature, range: 220 - 260°C

Mold temperature, range: 30 - 80°C