

**Product Texts**

Terluran® GP-35 is a high-flow, general purpose injection molding grade with good ductility, intended for moldings with thin walls and/or adverse flow length to wall ratio.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>34</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>220</b>	°C	-
Load	<b>10</b>	kg	-
<sup>[C]</sup> Density of melt	<b>934</b>	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	<b>0.18</b>	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	<b>2300</b>	J/(kg K)	-
<sup>[C]</sup> Ejection temperature	<b>84</b>	°C	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>2300</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>44</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>2.4</b>	%	ISO 527
<sup>[C]</sup> Nominal strain at break	<b>12</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>125</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>90</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>19</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>92</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>95</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	<b>95</b>	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Yellow Card available	<b>yes</b>	-	-
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-
Yellow Card available	<b>yes</b>	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	<b>&gt;1E13</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>1E13</b>	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>0.95</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.24</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1040</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Melt temperature	<b>220 - 260</b>	°C	-
Mold temperature	<b>30 - 60</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Platable

**Delivery form**

Pellets

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Additives**

Lubricants

**Other text information****Injection molding**

## PREPROCESSING

Pre-drying, Temperature: 80°C

Pre-drying, Time: 2 - 4h

## PROCESSING

Melt temperature, range: 220 - 260°C

Mold temperature, range: 30 - 80°C